

# LAC 900

EN  
12641-2



900 g/m<sup>2</sup>



3m







Gama  
kolorów

# LAC 900

		REF.	RAL	M	M*B	REF.	RAL	M	MB
<b>Nośnik</b> <i>Support / Trägergewebe / Soporte / Supporto</i>	1100 dtex PES HT	810	9005	3,00	30-60-200	7446	3002	3,00	30-60-200
<b>Powłoka</b> <i>Enduction / Beschichtung / Revestimiento / Spalmatura</i>	PVC (Lowick)	7196	7037	3,00	30-60-200	7523		3,00	30-60-200
<b>Wykończenie</b> <i>Finition / Ausstattung / Acabado / Finizione</i>	Cleangard	7300	9006	3,00	30-60-200	7446	3020	3,00	30-60-200
<b>Waga całkowita</b> <i>Poids Total / Gesamtgewicht / Peso total / Peso totale</i>	900 g/m <sup>2</sup>	939		3,00	30-60-200	7523	2004	3,00	30-60-200
<b>Wytrzymałość na zerwanie</b> > NF EN ISO 1421 <i>Résistance rupture / Reissfestigkeit / Resistencia a la rotura / Resistanza alla rottura</i>	400/400 daN	7374	7038	3,00	30-60-200	7445	2008	3,00	30-60-200
<b>Wytrzymałość na rozdarcie</b> > DIN 53363 <i>Résistance déchirure / Weiterreissfestigkeit / Resistencia al desgarro / Resistenza allo strappo</i>	60/50 daN	7459	7035	3,00	30-60-200	7456	1003	3,00	30-60-200
<b>Przyczepność</b> > NF EN ISO 2411 <i>Adhérence / Haftung / Adherencia / Aderenza</i>	10 daN / 5 cm	7452	6018	3,00	30-60-200	7445	1021	3,00	30-60-200
<b>Wytrzymałość na temperaturę</b> > NF EN 1876-2 <i>Temperatures d'utilisation / Temperaturbeständigkeit / Resistencia máxima a la temperatura / Resistenza alla temperatura</i>	-30°C +70°C	995	6026	3,00	30-60-200	7440	1018	3,00	30-60-200
<b>Ognioodporność</b> > DIN 75200 <i>Ignifugation / Brennverhalten / Ignifugación / Ignifugazione</i>	< 100 mm/min	7491		3,00	30-60-200	7443	1014	3,00	30-60-200
		7454	6028	3,00	30-60-200	7458	1015	3,00	30-60-200
		7451	6005	3,00	30-60-200	7455	9016	3,00	30-60-200
		7309	5013	3,00	30-60-200	867	9010	3,00	30-60-200
		7448	5003	3,00	30-60-200				
		7290	5002	3,00	30-60-200				
		941		3,00	30-60-200				
		7307	5010	3,00	30-60-200				
		7486		3,00	30-60-200				
		7492		3,00	30-60-200				
		7450	5015	3,00	30-60-200				
		7449	5012	3,00	30-60-200				

Zgodny z normą : EN 12641-2

-  Conforme à la norme : EN 12641-2
-  Entspricht : EN 12641-2
-  Conforme a la norma EN 12641-2.
-  Conforme con : EN 12641-2

Wartości średnie, poza umowne  
Valeurs moyennes, non-contractuelles / Alle angegebenen Werte sind ca. Werte Valores  
medios y no contractuales / Questi valori medi non hanno valore contrattuale

SYSTEM  
LOWICK

MADE IN  
FRANCE



FINITION  
CLEANGARD

REACH  
COMPLIANCE



DICKSON COATINGS

415, Avenue de Savoie  
Saint Clair de la Tour  
F-38387 La Tour du Pin

Tel. (+33) 04 74 83 51 00  
Fax (+33) 04 74 83 51 01

[www.dickson-coatings.com](http://www.dickson-coatings.com)



GLEN RAVEN™

Glen Raven™ jest znakiem firmowym  
a Dickson® jest zarejestrowaną  
marką Glen Raven, Inc.